

28303d

283.03

Designer Note: Check with Materials prior to using this provision. Specifications require "A" quality aggregate for erosion control and sediment protection. This provision reduces the required quality to "B" but also increases the permitted soundness loss to 35%. It is intended for use in western areas of the District (approximate dividing line Rte. 97) in order to permit those local stone quarries to furnish this type aggregate. Specifications also require a filter fabric to be paid separately. Thickness of aggregate is to be 300 mm (12 inches).

AGGREGATE DITCH

Effective April 15, 1991

Revised October 15, 2001

This work shall be performed in accordance with Article 283.03 except the aggregate shall meet "B" quality per Article 1005.01 and that the sodium sulfate loss shall not exceed 35%.